

IN THE CLAIMS

Claims 6-19 are pending in this application. Claims 1-5 are withdrawn from further consideration in this pending application as follows:

1. (Withdrawn) A magnetic head comprising a single pole type head which includes a main pole and a return pole, wherein said main pole is composed of a magnetic layer on which a non-magnetic metal layer is formed and a non-magnetic insulator layer is formed on said non-magnetic metal layer.
2. (Withdrawn) The magnetic head according to claim 1, wherein said main pole is composed of a FeCo layer, a CoNiFe layer, or a multilayered film consisting of FeCo and non-magnetic layers.
3. (Withdrawn) The magnetic head according to claim 1, wherein said non-magnetic metal layer is made of NiCr, Cr, Ta, or TaW and said non-magnetic insulator layer is made of Al₂O₃.
4. (Withdrawn) The magnetic head according to claim 1, wherein said non-magnetic metal layer has a thickness falling within a range of 5-30 nm.
5. (Withdrawn) The magnetic head according to claim 1, wherein said main pole has an air-bearing surface of a trapezoid shape and said non-magnetic metal layer is formed on the surface of one of parallel sides, which is longer, of the trapezoid.
6. (Original) A method of fabricating a magnetic head comprising a single pole type head which includes a main pole and a return pole, said method comprising the steps of:
 - forming a magnetic layer which is processed to be said main pole;
 - forming a first non-magnetic metal layer and a non-magnetic insulator layer in order on said magnetic layer;
 - forming a first mask of a resist layer on said non-magnetic insulator layer;
 - shaping said non-magnetic insulator layer by reactive ion etching, using said first mask, thus forming a second mask; and

shaping said magnetic layer into a designed shape of said main pole, using the second mask.

7. (Original) The method of fabricating a magnetic head according to claim 6, wherein said magnetic layer is a FeCo layer, a CoNiFe layer, or a multilayered film consisting of FeCo and non-magnetic layers and etching gas that is used for said reactive ion etching includes Cl_2 or BCl_3 .
8. (Original) The method of fabricating a magnetic head according to claim 7, wherein said first non-magnetic metal layer is made of NiCr, Cr, Ta, or TaW and said non-magnetic insulator layer is made of Al_2O_3 .
9. (Original) The method of fabricating a magnetic head according to claim 6, wherein said first non-magnetic metal layer has a thickness falling within a range of 5-30 nm.
10. (Original) A method of fabricating a magnetic head comprising a single pole type head which includes a main pole and a return pole, said method comprising the steps of:
 - forming a magnetic layer which is processed to be said main pole;
 - forming a first non-magnetic metal layer, a non-magnetic insulator layer, and a second non-magnetic metal layer in order on said magnetic layer;
 - forming a first mask of a resist layer on said second non-magnetic metal layer;
 - shaping said second non-magnetic metal layer by ion milling, using said first mask, thus forming a second mask; shaping said non-magnetic insulator layer by reactive ion etching, using said second mask, thus forming a third mask; and
 - shaping said magnetic layer into a designed shape of said main pole, using said third mask.
11. (Original) The method of fabricating a magnetic head according to claim 10, wherein said magnetic layer is a FeCo layer, a CoNiFe layer, or a multilayered film consisting of FeCo and non-magnetic layers and etching gas that is used for said reactive ion etching includes Cl_2 or BCl_3 .

12. (Original) The method of fabricating a magnetic head according to claim 11, wherein said first non-magnetic metal layer is made of NiCr, Cr, Ta, or TaW and said non-magnetic insulator layer is made of Al_2O_3 .
13. (Original) The method of fabricating a magnetic head according to claim 10, wherein said first non-magnetic metal layer has a thickness falling within a range of 5-30 nm.
14. (Original) The method of fabricating a magnetic head according to claim 10, wherein said second non-magnetic metal layer is made of NiCr, Cr, Ta, TaW, Cu, or Au.
15. (Original) A method of fabricating a magnetic head comprising a single pole type head which includes a main pole and a return pole, said method comprising the steps of:
 - forming a magnetic layer which is processed to be said main pole;
 - forming a first non-magnetic metal layer, a non-magnetic insulator layer, and a second non-magnetic metal layer in order on said magnetic layer;
 - forming a first mask of a resist layer on said second non-magnetic metal layer;
 - shaping said second non-magnetic metal layer and said non-magnetic insulator layer by reactive ion etching, using said first mask, thus forming a second mask; and
 - shaping said magnetic layer into a designed shape of said main pole, using said second mask.
16. (Original) The method of fabricating a magnetic head according to claim 15, wherein said magnetic layer is a FeCo layer, a CoNiFe layer, or a multilayered film consisting of FeCo and non-magnetic layers and etching gas that is used for said reactive ion etching includes Cl_2 or BCl_3 .
17. (Original) The method of fabricating a magnetic head according to claim 16, wherein said first non-magnetic metal layer is made of NiCr, Cr, Ta, or TaW and said non-magnetic insulator layer is made of Al_2O_3 .
18. (Original) The method of fabricating a magnetic head according to claim 15, wherein said first non-magnetic metal layer has a thickness falling within a range of 5-30 nm.

19. (Original) The method of fabricating a magnetic head according to claim 15, wherein said second non-magnetic metal layer is made of NiCr, Cr, Ta, TaW, Cu, or Au.